Bosworth Trim Plus Instructions for Use

Trim Plus is a fast-setting, non-irritating PMMA temporary crown and bridge material formulated for extended use.

DIRECTIONS



 Take an impression with material of choice. (Recommended: Bosworth Supergel)



Complete tooth preparations. Take another impression from which the final crown or bridge is to be made. Match tooth shade to closest Trim Plus shade.



Cut peripheral border and interproximal areas for best fit.



 Mix powder and liquid until honey-like consistency. Approximate powder to liquid ratio is 6.3 g of powder to 3 ml of liquid. This amount would make 9 full jacket crowns.



Fill each tooth area within the impression where preparatory work has been done with Trim Plus acrylic.



 When Trim Plus gets dull, reseat the impression to return to its original position.



Leave in place for 30-90 seconds. Remove when first feels warm. When material is rubbery it may be removed from impression and trimmed. May be placed back into impression until fully set.



 Trim and polish as desired. Cement bridge or crown in place with a noneugenol cement.

NOTES

- Using Bosworth Gorilla Seal or Glaze saves polishing time. Gorilla Seal will bond directly to the temporary when cured with a halogen bulb.
- 2. Do not allow material to cure in mouth.
- 3. May be bench cured or placed in pressure pot (Recommend: Bosworth Pressure Pot).

CAUTION: Certain individuals may be sensitive to products containing acrylic.

Bosworth Company

Polymethyl Methacrylate Temporary Resin Acrylic

Bosworth Trim Plus

ORDERING INFORMATION



)(최(포) 42 g) rs

4 oz (118 ml) Liquid

REF 0921930 Standard Kit

0921931	1.5 oz (42 g) Powder Select Shade
0921931s	1.5 oz (42 g) Fast Set Powder Select Shade
0921936	4 oz (118 ml) Liquid Only
0921933	1 lb (454 g) Bulk Powder, Select Shade
0921933s	1 lb (454 g) Bulk Fast Set Powder, Select Shade
0921937	8 oz (236 ml) Liquid Only
ADDITIONAL B	BULK PACKAGING AVAILABLE.

TOOTH	SHADE C	ONVERSIONS
BOSWORTH	ATIV H	NEW HUE
59	B1	59
60	A1	60
61	B2	61
62	A2	62
65	D3	65
66	A3	66
67	B3	67
68		68
69	C2	69
77	B4	77
81	A3.5	81
87	A4	87
	C3	
	C4	
	D4	

AVAILABLE PO	OWDER SHADES
☐ B1 (59)	B3 (67)
A1 (60)	68
B2 (61)	C2 (69)
A2 (62)	☐ B4 (77)
D3 (65)	A3.5 (81)
A3 (66)	A4 (87)
☐ Incisal	

Bosworth Company

Please forward health & safety questions to:



The Bosworth Company
7227 North Hamilin Avenue
Skokle, IL Bodh-3999 USA or
P. Moore
Unit 3, Holidene Way
Seaham Grange Ind. Estate, Seaham
CO Dutham, \$17 OPU England
www.bosworth.com * hibinfo@bosworth.com





Flashpoint 50°F (10°C)

Made in USA 0813PR166

WORKING TIME: 3-4 minutes TOTAL SET TIME: 10 minutes