



IMPACT-20

INSTRUCTIONS

GENERAL DESCRIPTION

IMPACT-20 heat cure denture base resin made with cross-linked acrylic polymer. It is reinforced to increase its impact resistance and its flexibility. It does not contain cadmium to reduce the risk of allergic reactions and a multi-fibres process is used to produce a natural appearance. IMPACT-20 heat cure resin has a short dough time combined with an extra-long working time. **NOTE: IMPACT-20 POWDER IS DESIGNED TO WORK IN CONJUNCTION WITH DENPLUS 20 MINUTES LIQUID IN ORDER TO OBTAIN PERFECT DENTURES BY THE FAST CURING PROCESS. DO NOT USE A DIFFERENT LIQUID FOR THE 20 MIN BOILING.**

CONTRAINDICATIONS

IMPACT-20 resin is contraindicated for patients and users with a history of allergic reaction to methyl methacrylate monomer.

WARNINGS

20 MINUTES liquid contains polymerizable monomers which may cause skin sensitization (redness, irritation) or other allergic reactions in susceptible persons. Avoid vapor inhalation and do not swallow this product.

ADVERSE REACTIONS

Allergic contact dermatitis and other allergic reactions may occur in susceptible individuals. Residual monomer in fully cured materials can be minimized by soaking the cured prosthesis in warm water for several days.

Fine particulates will be generated when grinding cured acrylic resins. Eye, skin and respiratory irritation may occur if appropriate protective equipment are not used.

HEALTH AND SAFETY INFORMATION

Please refer to the Safety Data Sheets (SDS) for information on any hazardous properties before handling. As the liquid is not miscible with water, it should not be eliminated via the municipal sewerage system.

Table 1

Powder : Liquid ratio	3.3 : 1
Ratio (volume)	33 cc : 10 ml or 30 cc : 9 ml
Gel time	9 ± 1 minutes
Snap time	14 ± 1 minutes
Working time	at least 35 minutes
Weight equivalent	33 cc = 23.4 g
Processing methods:	
• 20 min boil	20min. @ 100 °C (212 °F)
• Short curing	1 ½ h @ 73 °C (163 °F) then ½ h @ 100 °C (212 °F)
Cooling methods:	
Fast cooling:	30 min. bench then 20 min. in water
Recommended cooling:	bench, to 25 °C (77 °F)

PREPARATION

A wax denture is fabricated in the usual manner. Apply Separap Plus liquid to all gypsum surfaces. Allow the liquid to dry through before the resin is packed.

MIXING OF POWDER AND LIQUID

Shake powder well. Use the powder : liquid ratio specified in table 1. **DO NOT MANIPULATE LIQUID NEAR AN OPEN FLAME.** Pour the required amount of liquid into a mixing jar, then add the recommended portion of powder. Using a clean metal spatula, mix thoroughly for about 15 seconds to obtain a homogeneous mixture. The resin requires approximately one minute to completely absorb the monomer. Cover the jar to prevent drying prior to packing.

IMPACT-20 resin requires less monomer by design. **DO NOT ADD LIQUID; EXCESS MONOMER SUBSTANTIALLY INCREASES THE TIME IT TAKES FOR THE ACRYLIC TO SET AND COULD GENERATE POROSITY.**

The following table provides an indication for various denture sizes:

Table 2

CASE	Ratio 3.4 :1	
	Powder	Liquid
Large	40 cc	12 ml
Average	30 cc	9 ml
Partial	20 cc	6 ml

DOUGH TIME AND WORKING TIME

Dough consistency should be reached in about 7 minutes at 23 °C. At this point the dough is no longer tacky and can be worked with hands into a homogeneous, putty-like mass. The recommended packing stage is when the dough reaches the "snap point", i.e., when stretched, the dough breaks cleanly with a clear, popping sound.

PROCESSING METHODS

For the 20 min boiling, immerse the flask in boiling water. Bring the water back to boil and continue for 20 minutes.

For the slow curing method, cure the denture at 73 °C (163 °F) for 1½ hours and then 30 minutes at 100 °C (212 °F).

Cool the flask before deflasking (see table 1). Trim and polish in the usual manner.

SHIPPING AND CARE

It is recommended to deliver the finished denture in a wet environment. Prosthesis must be cleaned regularly to reduce bacterial contamination.

REPAIR AND SOFT BASE

It is recommended to use DP-Repair materials that are available in the same shades as this heat cure resin.

To make a soft base, it is recommended to initiate the curing of the resin by packing it in a slightly warm flask. Maintain under pressure for about 1 hour to harden the resin. Afterwards, apply soft base according to manufacturer's instructions.

To order or for information:

DENPLUS Inc.

333-M Chemin du Tremblay, Boucherville, QC, Canada, J4B 7M1

Tel.: (450) 641-1330 or toll-free 1-888-344-4424

Fax: (450) 600-8309 or toll-free 1-888-481-0389

Email: info@denplus.com

www.denplus.com